



Fabric Specification: 2100 FR701®

Fabric type: Panel

Construction Specifications

Fiber Contents:		100% post-consumer recycled polyester
Yarns:	Warp:	Woolen Spun
	Fill:	Woolen Spun
Ends/inch:		17+/- 1
Picks/inch:		16+/-1
Weave type:		Plain
Width:		66" min. usable
Weight:		16+/-0.5 oz/lin. yd
Repeat:	Horizontal	Not applicable
	Vertical	Not applicable
Chemical finish/coatings:		None

Performance Specifications

Colorfastness to Light:
(AATCC 16 Option 3) Class 4 min. at 40 hr.

Colorfastness to Crocking:
(AATCC 8) Class 4 min. Dry
Class 3 min. Wet

Breaking Strength: (ASTM D5034)	Warp	150 lbf min.
	Fill	150 lbf min.

Tear Strength: (ASTM D2261)	Warp	30 lbf min.
	Fill	30 lbf min.

Flammability

ASTM E-84 Class 1 or A

Cleaning Code WS