



## Fabric Specification: 2120 Tempest

Fabric type: Panel

### Construction Specifications

Fiber Contents:		73% pre-consumer recycled polyester 27% post-consumer recycled polyester
Yarns:	Warp:	Filament
	Fill:	Filament
Ends/inch:		53+/-2
Picks/inch:		45+/-2
Weave type:		Dobby
Width:		66" min. usable
Weight:		11.3+/-1.0 oz/lin. yd
Repeat:	Horizontal	Not applicable
	Vertical	Not applicable
Chemical finish/coatings:		None

### Performance Specifications

Colorfastness to Light:  
(AATCC 16 Option 3) Class 4 min. at 40 hr.

Colorfastness to Crocking:  
(AATCC 8) Class 4 min. Dry  
Class 3 min. Wet

Breaking Strength: (ASTM D5034)	Warp	180 lbf min.
	Fill	160 lbf min.

Tear Strength: (ASTM D2261)	Warp	15 lbf min.
	Fill	15 lbf min.

### Flammability

ASTM E-84 Class 1 or A

Cleaning Code WS

TES-2120 Rev D

Effective date: September 11, 2009

Approval: Alan Dean

Page 1 of 1

5300 Corporate Grove Drive SE, Suite 250 Grand Rapids, MI 49512

Phone: 800.544.0200 Fax: 616.554.2255

Printed copies are uncontrolled unless stamped "Controlled" in red. See [www.true textiles.com](http://www.true textiles.com) for most recent revision.