



Fabric Specification: 2131 Cirrus

Fabric type: Panel

Construction Specifications

| | | |
|---------------------------|-------------|--|
| Fiber Contents: | | 60% Post-consumer recycled Polyester 40% Wool |
| Yarns: | Warp: | Woolen Spun |
| | Fill: | Woolen spun |
| Ends/inch: | | 23+/-1 |
| Picks/inch: | | 21+/-1 |
| Weave type: | | Plain |
| Repeat: | Horizontal: | Not applicable |
| | Vertical: | Not applicable |
| Width: | | 66" min. usable |
| Weight: | | 11.5+/-1.0 oz/lin yd |
| Chemical finish/coatings: | | None |

Performance Specifications

| | | |
|--|------|--------------------------------------|
| Colorfastness to Light: (AATCC 16 Option 3) | | Class 4 min. at 40 hr. |
| Colorfastness to Crocking: (AATCC 8) | | Class 4 min. Dry Class 3 min. Wet |
| Breaking Strength: (ASTM D5034) | Warp | 75 lbf min. |
| | Fill | 75 lbf min. |
| Tear Strength: (ASTM D2261) | Warp | 15 lbf min. |
| | Fill | 15 lbf min. |

Flammability

ASTM E84 Class A or 1

Cleaning Code WS

TES-2131 Rev B

Effective date: January 14, 2009

Approval: Alan Dean

Page 1 of 1

5300 Corporate Grove Drive SE, Suite 250 Grand Rapids, MI 49512

Phone: 800.544.0200 Fax: 616.554.2255

Printed copies are uncontrolled unless stamped "Controlled" in red. See www.true textiles.com for most recent revision.