



## Fabric Specification: 2314 Phone Tag

Fabric type: Panel

### Construction Specifications

Fiber Contents:		21% pre-consumer recycled polyester 79% post-consumer recycled polyester
Yarns:	Warp:	Filament
	Fill:	Filament and Woolen spun
Ends/inch:		42+/-2
Picks/inch:		33+/-1
Weave type:		Dobby
Width:		66" min. usable
Weight:		14.0+/-1.0 oz/lin. yd
Repeat:	Horizontal	Not applicable
	Vertical	Not applicable
Chemical finish/coatings:		None

### Performance Specifications

Colorfastness to Light:  
(AATCC 16 Option 3) Class 4 min. at 40 hr.

Colorfastness to Crocking:  
(AATCC 8) Class 4 min. Dry  
Class 3 min. Wet

Breaking Strength: (ASTM D5034)	Warp	150 lbf min.
	Fill	110 lbf min.

Tear Strength: (ASTM D2261)	Warp	25 lbf min.
	Fill	25 lbf min.

### Flammability

ASTM E-84 Class 1 or A

Cleaning Code WS

TES-2314 Rev B  
Effective date: July 8, 2009  
Approval: Alan Dean

Page 1 of 1

5300 Corporate Grove Drive SE, Suite 250 Grand Rapids, MI 49512  
Phone: 800.544.0200 Fax: 616.554.2255

Printed copies are uncontrolled unless stamped "Controlled" in red. See [www.truetextiles.com](http://www.truetextiles.com) for most recent revision.