



## Fabric Specification: 2335 Anchorage

**Fabric type:** Panel

### Construction Specifications

Fiber Contents:		100% recycled polyester
Yarns:	Warp:	Filament
	Fill:	Filament
Ends/inch:		44+/-2
Picks/inch:		43+/-2
Weave type:		Crepe
Width:		66" min. usable
Weight:		15.0+/-1.0 oz/lin. yd
Repeat:	Horizontal	Not applicable
	Vertical	Not applicable
Chemical finish/coatings:		None

### Performance Specifications

Colorfastness to Light:  
(AATCC 16 Option 3) Class 4 min. at 40 hr.

Colorfastness to Crocking:  
(AATCC 8) Class 4 min. Dry  
Class 3 min. Wet

Breaking Strength: Warp 275 lbf min.  
(ASTM D5034) Fill 275 lbf min.

Tear Strength: Warp 35 lbf min.  
(ASTM D2261) Fill 35 lbf min.

### Flammability

ASTM E-84 Class 1 or A

**Cleaning Code** WS