



Fabric Specification: 2539 Drift

Fabric type: Panel

Construction Specifications

Fiber Contents:		51% post-consumer recycled polyester 49% pre-consumer recycled polyester
Yarns:	Warp:	Filament
	Fill:	Woolen spun
Ends/inch:		138+/-4
Picks/inch:		31+/-2
Weave type:		Jacquard
Repeat:	Horizontal:	14"
	Vertical:	9.6"
Width:		66" min. usable
Weight:		12.0+/-1.0 oz/lin yd
Chemical finish/coatings:		None

Performance Specifications

Colorfastness to Light:
(AATCC 16 Option 3) Class 4 min. at 40 hr.

Colorfastness to Crocking:
(AATCC 8) Class 4 min. Dry
Class 3 min. Wet

Breaking Strength: (ASTM D5034)	Warp	250 lbf min.
	Fill	125 lbf min.

Tear Strength: (ASTM D2261)	Warp	15 lbf min.
	Fill	15 lbf min.

Flammability

ASTM E84 Class A or 1

Cleaning Code WS

TES-2539 Rev B
Effective date: January 19, 2009
Approval: Alan Dean

Page 1 of 1

5300 Corporate Grove Drive SE, Suite 250 Grand Rapids, MI 49512
Phone: 800.544.0200 Fax: 616.554.2255

Printed copies are uncontrolled unless stamped "Controlled" in red. See www.truetextiles.com for most recent revision.