



Fabric Specification: 2670 Otto

Fabric type: Panel

Construction Specifications

Fiber Contents:		34% post-industrial recycled polyester 31% post-consumer recycled polyester 35% polypropylene
Yarns:	Warp:	Filament
	Fill:	Filament and spun
Ends/inch:		54 +/-2
Picks/inch:		17 +/-1
Weave type:		Dobby
Width:		66" min. usable
Weight:		13.5 +/- 0.5 oz/lin yd
Repeat:	Horizontal	Not applicable
	Vertical	Not applicable
Chemical finish/coatings:		Polyester binder

Performance Specifications

Colorfastness to Light:
(AATCC 16 Option 3) Class 4 min. at 40 hr.

Colorfastness to Crocking:
(AATCC 8) Class 4 min. Dry
Class 3 min. Wet

Breaking Strength: (ASTM D5034)	Warp	200 lbf min.
	Fill	175 lbf min.

Tear Strength: (ASTM D2261)	Warp	40 lbf min.
	Fill	40 lbf min.

Flammability

ASTM E84 Class A or 1

Cleaning Code WS

TES-2670 Rev A

Effective date: January 5, 2009

Approval: Alan Dean

Page 1 of 1

5300 Corporate Grove Drive SE, Suite 250 Grand Rapids, MI 49512

Phone: 800.544.0200 Fax: 616.554.2255

Printed copies are uncontrolled unless stamped "Controlled" in red. See www.true textiles.com for most recent revision.