



Fabric Specification: 3583 Zirconia

Fabric type: Panel

Construction Specifications

Fiber Contents:		86% pre-consumer recycled polyester 14% post-consumer recycled polyester
Yarns:	Warp:	Filament
	Fill:	Filament and woolen spun
Ends/inch:		73+/-2
Picks/inch:		40+/-2
Weave type:		Jacquard
Repeat:	Horizontal:	16.5"
	Vertical:	16.0"
Width:		66" min. usable
Weight:		12.4+/-1.0 oz/lin yd
Chemical finish/coatings:		None

Performance Specifications

Colorfastness to Light: (AATCC 16 Option 3)		Class 4 min. at 40 hr.
--	--	------------------------

Colorfastness to Crocking: (AATCC 8)		Class 4 min. Dry Class 4 min. Wet
---	--	--------------------------------------

Breaking Strength: (ASTM D5034)	Warp	240 lbf min.
	Fill	100 lbf min.

Tear Strength: (ASTM D2261)	Warp	25 lbf min.
	Fill	25 lbf min.

Flammability

ASTM E84		Class A or 1
----------	--	--------------

Cleaning Code		WS
---------------	--	----